

H6909 PermaTop Data Sheet

Subject	Result	Test Method
Film	Homogenous transparent PVC	N/A
Film thickness	0.6mm	Calliper Method
Adhesive type	Modified solvent acrylic	N/A
Peel adhesion to stainless steel, 20 minute dwell, N/25mm	25.2	FINAT FTMI
Peel adhesion to stainless steel, 24 hour dwell, N/25mm	28.0	FINAT FMI
Tensile strength, N/25mm	158	Lloyd T5100 with 500N load cell
Elongation at break	294%	Lloyd T5100 with 500N load cell
Colour	Transparent	N/A
Temperature Range	-30°C to +70°C	N/A
Maximum size of the production roll	1260mmx100m	N/A

The above tests were performed by Adhesive Technical Services Ltd, original test data available on request.

Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
Pendulum	102	24
DIN51130	R10	

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H6909 (Clear)	Transparent	Transparent	66.3	47.7

©Heskins Ltd 1997-2024