

3418 Handrail Grip Tape Data Sheet

Subject	Result
Composition	PVC upper and PET base
Total applied thickness	0.04 in
Adhesive thickness	0.004 in
Material thickness	0.31 in
Total thickness	0.04 in
Type of adhesive	Solvent acrylic
Tack loop (lb/in)	13.78
Cohesion (minutes/77°F)	2812↑
Adhesion to steel (lb/in)	12.6
Maximum size of production roll	37 ft x 328 ft
Life (months)	24

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
3418 (Black)	7021	Black U	1	2

Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
3418	92	25
Rz	59.3	

The above tests were conducted in accordance with CTIOA pendulum method using a four S rubber slider, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request. CTIOA is a dynamic test, for static tests we also have results conducted via ASTM C 1028-96.

All the above data is for reference only.

©Heskins Ltd 1997-2024