

## 3452 Premium Photoluminescent Coarse Resilient Data Sheet

Subject	Test method
Composition	Composite construction
Type of adhesive	Solvent acrylic
Overall thickness (in)	0.06 in
Tackloop (lb/in)	6.35
Cohesion (mins/77°C)	4320
Adhesion to steel (lb/in)	5.07
Temperature range	14°F ~ 176°F
Maximum roll size	48in x 164ft
Life (months)	12 to 24
Glow Time	8~10 hours

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

### Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
3452 Coarse Resilient	95 TRL	60 TRL

	Coefficient of Friction Category	Test
3452 Coarse Resilient	R10	DIN51130

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

### LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
3452 (Photoluminescent)			48.5	4

### Photoluminescent data

Time	Luminance mcd/m²	Test date
10 minutes	299	04/15/15
60 minutes	40	04/15/15

All the above data is for reference only.

©Heskins Ltd 1997-2024

