



ANTI-SLIP SOLUTIONS
mail@heskins.us

www.heskins.us

04/04/2024

Fluorescent base for SMV signs

Physical Characteristics

	Test Method	Typical Value
Film Thickness	ISO 4591:1992	100µm
Elongation	ISO 527:1996	>75%

Adhesive Properties

Adhesive Type	Pigmented
Adhesive Thickness	40g/m ²
Adhesion to painted steel 20 Mins/180°	>380 N/m
Adhesion to painted steel 24 Hrs/180°	>530 N/m
Release Liner	PE Coated
Widths	48 inches

Durability

Flammability		Self-Extinguishing
Artificial Weathering	Atlas Xenon Arc	>250 hours Fluorescents
Durability is based on middle European exposure conditions		
Service Temperature -40°F to 194°F		

All the above data is for reference only.

©Heskins LLC 1997-2024



ISO 9001

