

GID1616 Photoluminescent Warehouse Marker Data Sheet

Subject	Result	Test Method
Material	Under surface printed OPP	N/A
Type of adhesive	Solvent acrylic (0.0004in)	N/A
Film thickness	0.0016in	N/A
Adhesive thickness	0.0071in	N/A
Total thickness	0.0087in	PSTC-6
Temperature range	-22°F ~ +158°F	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Luminance Test	
Time (minutes)	Luminance (mcd/m ²)
2	478.4
10	95.1
30	27.7
60	12.17
Decay time (to 0.3mcd/m ²)	1450 mins

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS:8493:2008+A1:2010

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
H7801 (Green)	6029	3536	55.6	1.4
H7801 (GID)	9010	White	89.9	1.7

All the above data is for reference only.

©Heskins Ltd 1997-2024