

## LEAN PermaLean Data Sheet

Subject	Result	Test Method
Film	Homogenous coloured PVC	N/A
Film thickness	0.02IN	Calliper Method
Adhesive type	Modified solvent acrylic	N/A
Adhesive thickness	0.0047in	N/A
Total thickness	0.024in	N/A
Peel adhesion to stainless steel, 20 minute dwell, lbf/in	5.76	FINAT FTMI
Peel adhesion to stainless steel, 24 hour dwell, lbf/in	6.39	FINAT FMI
Tensile strength, lbf/in	36.1	Lloyd T5100 with 112 lbf load cell
Elongation at break	294%	Lloyd T5100 with 112 lbf load cell
Color	Standard colors are black, orange, red, green, white and yellow. Any Pantone or RAL color can be produced dependent on MOQ	N/A
Temperature Range	-22°F to +158°C	N/A
Maximum size of the production roll	49in x 328ft	N/A

The above tests were performed by Adhesive Technical Services Ltd, original test data available on request.

	Dry Surface Test Result	Wet Surface Test Result
Pendulum	102	24
DIN51130	R10	

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request.

## LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
LEAN_N (Black)	9004	Black 6 U	3.1	0.8
LEAN_R (Red)	3001	484 U	13.4	0.5
LEAN_O (Orange)	2010	1665 U	23.1	0.3
LEAN_Y (Yellow)	1003	137 U	52.3	1
LEAN_V (Green)	6032	3288 U	14.9	0.8
LEAN_B (Blue)	5005	294 U	6.6	0.4
LEAN_W (White)	9003	705 U	78.1	0.8
LEAN_D (Yellow/ Black Hazard)	9004 / 1003	Black 6 U / 137 U	3.2 / 62.9	0.8
LEAN_E (Black/ White Hazard)	9004 / 9003	Black 6 U / 7541 U	3.1 / 78.1	0.8 / 0.8
LEAN_A (Red/ White Hazard)	3028 / 9003	32 U / White	25.8 / 78.6	1.1 / 1.9

All the above data is for reference only.

©Heskins Ltd 1997-2024

