

## 6902ESD ESD Printed Floor Marking Tape (PermaRoute) Data Sheet

Subject	Result	Test Method
Top laminate	0.022in clear PVC	N/A
Bottom carrier	0.0059in PVC	N/A
Total thickness, with adhesive	0.038in	N/A
Adhesion type	Solvent acrylic	N/A
Tack loop (lb/in)	13.2	PSTC-16
Cohesion (hrs/77°F)	24↑	ASTM-7
Adhesion to steel (lb/in)	13.2	PSTC-1
Temperature range	-22°F to +158°F	See notes below
EN 13501/DIN 11925	Pass	Exova certificate 2012-1552-1

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England.

### Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Results
Pendulum	102	24
DIN51130	R10	

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request.

### Conductive Performance

OHMS per square	10 <sup>11</sup>
-----------------	------------------

### LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
6902ESD (Black)	9004	Black 6 U	3.6	1.8
6902ESD (Yellow)	1018	114 U	43.3	1.3
6902ESD (White)	9003	7541 U	61.8	4.1

All the above data is for reference only.

©Heskins LLC

