

7502 Warehouse Markers Data Sheet

Subject	Result	Test Method
Material	PVC laminated with DST	N/A
Type of adhesive	Solvent acrylic (0.0032in)	N/A
PVC	0.001 in rigid film	N/A
DST	0.0037in	N/A
Initial tack (in)	4.7	PSTC-6
Peel adhesion (lb/in)	2.9	PSTC-1
Holding power (hr/in ²)	1↑	PSTC-7
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Temperature range	-22°F ~ +158°F	See notes below

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
7502 (Orange)	1032	7408 U	43.7	1.6
7503 (Orange/Black)	7021 / 1032	Black U / 7408 U	4 / 39.6	1 / 2.5

All the above data is for reference only.

©Heskins LLC