

CON Conformable Anti-Slip Traction Tape Data Sheet

Subject	Result	Test Method
Back carrier	Soft Aluminum 0.003 in	Calliper method
Total applied thickness	0.04 in	Calliper Method
Type of adhesive	Solvent Acrylic	N/A
Peel adhesion lbf/in	4.04	180° FINAT FTMI
Tensile strength, lbf/in	33.92	Lloyd, 112 lbf load cell
Fire retardancy	Pass	CAA/FAA spec 8
Mineral type	Aluminium Oxide	N/A
Adhesion to Steel (psi)	3.95↑	PSTC-4
Colour	All available Pantone® or RAL® standard colors are black, yellow, black/yellow, orange and white	N/A
Temperature range	-40°F to +320°F	N/A
Maximum size of the production roll	39in x 328ft	N/A

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
CON_N (Black)	9004	Black U	0	0
CON_O (Orange)	2004	021 U	18.3	3
CON_Y (Yellow)	1023	115 U	37.5	3
CON_W (White)	9003	White	72.3	1
CON_D (Black/Yellow Hazard)	9017 / 1003	Black U / 115 U	0 / 43.5	0 / 4

Coefficient of Friction Data

Safety-Grip™ EN16165:2021 Pendulum Test Value (PTV)	Dry Surface Test Result	Wet Surface Test Result
	0.99	0.75

The above tests were conducted in accordance with Pendulum BS7976-2 using a TRL slider. Pendulum is a dynamic test, for static tests we also have ASTM C10128-96. DIN51 130 results available on request. All tests are performed externally at recognized independent friction testing laboratories.

©Heskins LLC

