

CUSH Cushion Grip Data Sheet

Subject	Result
Components	PU51% Polyester 49%
Color	Gray
Adhesive base	Acrylic
Thickness	1mm
Initial tack	20# Ball
Applied weight	2.1 oz/ft ²
180° Peel adhesion	3.3 lb/in
Holding power 77°F	1 in 2.2 lb > 24hrs
Temperature range	-14°F ~ 176°F
Bursting strength	142 psi
Abrasion stoll	800 Cycles
Elongation	Without PET: 10% With PET: 5%

Coefficient of Friction Data

Test	Dry Surface Test Result	Wet Surface Test Result	Test Standard
Pendulum (PTV)	1.02	0.71	EN 13036-4

The tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request.

LRV Test Results

SKU/Color	RAL	Pantone	Av. LRV	Range
CUSH_S/Gray	7046	431 U	20.3	2

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins LLC