

## FIRE Fire Exit Marker Data Sheet

Subject	Result	Test Method
Back carrier	0.004 in PVC	Caliper method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Aluminium Oxide	N/A
Adhesion to steel (oz/in <sup>2</sup> )	1344↑	PSTC-4
Tensile strength (lb/in <sup>2</sup> )	336↑	PSTC-31
Tear resistance (oz)	198 +/- 7	PSTC-39
Elongation at break	25%↑	PSTC-31
Temperature range	-22°F to +158°F	See notes below
Size	Either 3.3ft x 3.3ft or 3.3ft x 5ft	N/A
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

### LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
FIRE (Black /Yellow)	9004 / 1023	Black U / 113U	3.8 /42.5	0.2 / 0.6

### Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
H3416	102 TRL	71 TRL

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

All the above data is for reference only.

©Heskins LLC