

PEAK PeakGrip Data Sheet

Subject	Result	Test method
Back carrier	0.0003in PVC	Caliper method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Silicon carbide	N/A
Adhesion to steel (24 hours. Lbf/in)	3.31↑	PSTC-101
Tensile strength (lbf/in)	8.82↑	ASTM D882-02
Temperature range	-22°F to +158°F	See notes below
Maximum size of production roll	46in x 60ft	N/A
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Coefficient of Friction Data

Safety-Grip™	Dry Surface Test Result	Wet Surface Test Result
PEAK Tested with Pendulum (PTV), EN16165, BS7976 4S rubber	69	67

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
H3456_N (Black)	9005	Black U	0.46	0.72

All the above data is for reference only.

©Heskins LLC