

Heskins RLGP RollerGrip data sheet

Subject	Result	Test Method
Backing material	Silicone coated cloth	N/A
Total applied thickness	0.62mm (0.024")	Calliper method
Type of adhesive	Solvent acrylic	N/A
Peel adhesion N/25mm 20 minute dwell	14.5	180° FINAT FTMI
Peel adhesion N/25mm 24 hour dwell	16.8	180° FINAT FTMI
Temperature range	-40°F to +212°F	See notes below
Maximum size of Production roll	15.7"x330'	N/A

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H5301S (Grey)	7047	420 CP	37.8	5.49

All the above data is for reference only.

©Heskins LLC