

540I 0.079in Thick Coarse Resilient Data Sheet

Subject	Result
Composition	PVC upper and PET base
Type of adhesive	Solvent acrylic
Overall thickness (in)	0.079in
Tackloop (psi)	13.73
Cohesion (minutes/77°F)	2812↑
Adhesion to steel (psi)	12.597
Temperature range	-14°F ~ 176°F
Maximum roll size	53in x 328ft
Life (months)	12 to 24

Coefficient of Friction Data (CoF)

	Dry Surface Test Result	Wet Surface Test Result
540I Coarse Resilient	95 TRL	60 TRL

	CoF Category	Test
540I Coarse Resilient	R10	DIN51130

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
540IN (Black)	9004	Black 7 U	1.7	0.7
540IY (Yellow)	1023	115 U	55.5	1.5
540IB (Blue)	5017	3005 U	6.4	0.7
540IS (Gray)	7046	428 U	5.8	0.8

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins LLC