

WALKWAY Walkway System Data Sheet

Subject	Result	Test Method
Back carrier	0.004 in PVC	Caliper method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Aluminium Oxide	N/A
Adhesion to steel (psi)	84↑	PSTC-4
Tensile strength (psi)	336↑	PSTC-3 I
Tear resistance (oz)	198 +/- 7	PSTC-39
Elongation at break	25%↑	PSTC-3 I
Temperature range	-7.6°F to +158°F	See notes below
Size	Either 3.3ft x 16.40 ft or 3.3 ft x 33 ft	N/A
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

LRV Test Results

SKU (Color)	RAL	Pantone	Av. LRV	Range
3416 (Green)	6010	342 U	7.5	0.3
3416 (Yellow)	1023	113 U	42.5	0.6

Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
3416	102 TRL	71 TRL

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognized independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins LLC