

## 3467 HoldGrip Non-Abrasive Anti-Slip Tape Data Sheet

Subject	Result	Test method
Upper film	PVC	N/A
Upper film thickness	0.06in	Caliper method
Base laminate	PET	N/A
Base film thickness	0.0008in	Caliper method
Type of adhesive	Solvent acrylic	N/A
Adhesive thickness	0.004in	Caliper method
Total thickness	0.06in	Caliper method
Type of adhesive	Solvent acrylic	N/A
Release film	White kraft paper	N/A
Pattern	Pattern modified emboss	N/A
Peel adhesion to stainless steel, 20 minute dwell Lbf/in	6.4	FINAT FTMI
Peel adhesion to stainless-steel, 24-hour dwell Lbf/in	5.708	FINAT FTMI
Application Temperature	-40°F ~ 176°F	N/A
Maximum size of production roll	50in x 66f	N/A
Life (months)	12 to 24	PSTC-9

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

### Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
H3467	92	25
Rz	59.3	

The above tests were conducted in accordance with CTIOA pendulum method using a four S rubber slider, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. CTIOA is a dynamic test, for static tests we also have results conducted via ASTM C 1028-96.

All the above data is for reference only.

©Heskins LLC

